

**ADVANTAGE REFINISH PRODUCTS®**  
**TECHNICAL DATA INFORMATION**  
**DATED: JULY 2016**

<b>PRODUCT NUMBER</b>	<b>DESCRIPTION</b>	<b>SIZE</b>
#801-01	Economy Lightweight Bodyfiller	Gallon

**PRODUCT DESCRIPTION:**

ADVANTAGE #801 Lightweight Filler is a creamy body filler with a smooth texture that is easy to spread and sands to a fine featheredge. The tack free, clog free and non-sag formula is perfect for repairing vertical surfaces.

**PRODUCT USES:**

Use for filling and repair of bodywork up to 1/4", such as dents, dings, scratches, hail damage and small holes.

**TYPICAL SUBSTRATES:**

- Steel
  - Aluminum
  - Fiberglass
  - Body Filler
  - Wood
  - 2K Primers
  - Aged, sanded OEM Topcoats
  - Galvanized and other zinc-coated steel
- SMC – can be used for cosmetic repairs. For structural repairs prone to high degrees of stress and flexibility, use an SMC repair product.

**SURFACE PREPARATION:**

1. Clean surface. Remove all dirt, oil, grease and wax with a cleaning solvent like Wax & Grease Remover.
2. Make sure surface is dry before repairing.
3. Use 40-80 grit disc to featheredge paint for good mechanical adhesion.

**MIXING DIRECTIONS:**

For best results, bring filler and provided hardener to room temperature (minimum temperature 75°F). Stir product before dispensing with a bottom to top motion. Knead hardener tube before use. Place a 4" diameter puddle of filler on a clean mixing surface (we recommend a non-absorbent plastic mixing board) and add a ribbon of cream hardener from edge to edge across the center of the filler puddle (puddles larger than 4" will require additional hardener); or measure hardener at 2% by weight of filler – a 50 to 1 ratio. Mix thoroughly with a plastic spreader, using a folding motion, until uniform color is achieved. At room temperature (75°F) approximate setting time is 3 – 5 minutes.

**APPLICATION DIRECTIONS:**

1. Using a plastic spreader, apply a thin layer of filler to surface, using firm pressure for maximum adhesion.
2. Apply additional layers, if necessary, building up damaged area higher than

surrounding metal surface to allow for sanding of filler.

**3. IMPORTANT! DO NOT RETURN UNUSED MIXTURE TO CAN AS IT WILL HARDEN THE REMAINING CONTENTS.**

**FINISHING:**

1. When material has cured, in approximately 15 minutes, sand with a 80-120 grit sandpaper.
2. Finish sand with 180-240 grit.

**TOPCOATING:**

May be topcoated with polyester, 2K urethane or 1K primer. Refer to paint manufacturer's instructions for topcoat application.

**TECHNICAL INFORMATION:**

Appearance as Packaged:	Off-White
VOC:	Packaged: 215 g/l - Applied: 0.8 g/l
Weight Per Gallon (Density):	9.7 pounds (Average)
Maximum Recommended Thickness (sanded):	1/4"
Viscosity @ 77°F:	96,000 cps (Average)
Gel Time @ 77°F:	3.0 – 5.0 minutes
Shore "D" Hardness Values @ 24 hours:	50-60
Sanding Time @ 77°F:	15-20 minutes
Maximum Heat:	200°F for 30 minutes
Catalyst Required:	Benzoyl Peroxide
Catalyzation Ratio:	2% by weight
Exotherm Temperature:	200°F (Average)
Tack Free Time:	10 – 15 minutes

**HEALTH & SAFETY:**

Read all warnings, first aid and safety for all components before using. Keep out of reach of children and animals. Protect hands with impervious rubber gloves. Wear face, skin and eye protection. When sanding, we recommend the use of a respiratory covering device to protect from dust (MSA mask P/N 459029 with MSA cartridge 464029 or equivalent). When using power equipment, refer to power tool manufacturer's recommendations for safety equipment.

**ADVANTAGE REFINISH PRODUCTS® are for industrial use by trained professionals only.**

**Emergency Medical or Spill Control Information:**

In U.S. and Canada call CHEMTREC at 1-800-424-9300

**WWW.ADVANTAGEREFINISH.COM**

